



(19)

(11) Publication number:

07292846 A

Generated Document.

PATENT ABSTRACTS OF JAPAN(21) Application number: **06089843**(51) Intl. Cl.: **E04C 2/04 B28B 1/50 B28B 23/02 C04B 38/02 E04C 2/06**(22) Application date: **27.04.94**

(30) Priority:

(43) Date of application
publication: **07.11.95**(84) Designated contracting
states:(71) Applicant: **SEKISUI CHEM CO LTD**(72) Inventor: **SAKOTA HIROMI
NOZAKI ZENJI
YAMAMOTO MASAHIITO**

(74) Representative:

**(54) EXTERNAL WALL
PANEL AND PRODUCTION
THEREOF**

(57) Abstract:


PURPOSE: To reduce the weight and increase the load-resistance, by laminating decoration materials and unify them on one side face of a base material obtained by foaming an inorganic foaming composition made of fly ash powder, alkali metal silicate, water and a foaming agent.

CONSTITUTION: A foaming inorganic composition is prepared, which is composed of 100 pts.wt. of fly ash powder containing 80% or more powder having 10 μ m or finer particle size, 0.2-450 pts.wt. of alkali metal silicate, 35-1500 pts.wt. of water and foaming agent. A decoration material 1 is placed upside down on the bottom of a lower mold and reinforcements are positioned in the upper mold. After the foaming inorganic composition has been charged on the rear face of the decoration material 1, the mold is

BEST AVAILABLE COPY

closed and heated at 50-100°C to foam the composition. After curing, it is removed from the mold to form an external wall panel 10.

COPYRIGHT: (C)1995,JPO



BEST AVAILABLE COPY

THOMSON
DELPHION

RESEARCH

PRODUCTS

INSIDE DELPHION

My Account | Products

Search: Quick/Number Boolean Advanced Derwent

The Delphion Integrated View

Get Now: ☒ PDF | [More choices...](#)Tools: Add to Work File: ☐ Create new Work File ☒ GoView: [INPADOC](#) | Jump to: [Top](#) ☒ Go to: [Derwent](#)☒ [Email this to a friend](#)

Title: JP7292846A2: EXTERNAL WALL PANEL AND PRODUCTION THEREOF

Derwent Title: Exterior wall - comprises base material contg. fly ash powder, alkali metal silicate, water and blowing agent, with decorative and reinforcing materials
[Derwent Record]

Country: JP Japan

Kind: A

Inventor: SAKOTA HIROMI;
NOZAKI ZENJI;
YAMAMOTO MASAHIRO;

Assignee: SEKISUI CHEM CO LTD
[News, Profiles, Stocks and More about this company](#)

Published / Filed: 1995-11-07 / 1994-04-27

Application Number: JP1994000089843

IPC Code: [E04C 2/04](#); [B28B 1/50](#); [B28B 23/02](#); [C04B 38/02](#); [E04C 2/06](#);

Priority Number: 1994-04-27 JP1994000089843


Abstract: PURPOSE: To reduce the weight and increase the load-resistance, by laminating decoration materials and unify them on one side face of a base material obtained by foaming an inorganic foaming composition made of fly ash powder, alkali metal silicate, water and a foaming agent.

CONSTITUTION: A foaming inorganic composition is prepared, which is composed of 100 pts.wt. of fly ash powder containing 80% or more powder having 10µm or finer particle size, 0.2-450 pts.wt. of alkali metal silicate, 35-1500 pts.wt. of water and foaming agent. A decoration material 1 is placed upside down on the bottom of a lower mold and reinforcements are positioned in the upper mold. After the foaming inorganic composition has been charged on the rear face of the decoration material 1, the mold is closed and heated at 50-100°C to foam the composition. After curing, it is removed from the mold to form an external wall panel 10.

COPYRIGHT: (C)1995,JPO

Family: None

Other Abstract Info: CHEMABS 124(08)095641A CAN124(08)095641A DERABS C96-017764
DERC96-017764



[View Image](#)

1 page



[Nominate](#)

[this for the Gallery...](#)

BEST AVAILABLE COPY